

Stainless steel electrode

Classification

AWS A5.4-92 : E318-15*
 EN 1600-97 : E 19 12 3 Nb B 22

Temperature Range

* Deviation: see remarks

General description

Basic coated electrode for stabilized CrNiMo-steels
 Service temperatures up to 400°C
 Good bridging properties
 Specially developed for highly restrained structures

Welding positions



Current type

DC electr. + / -

Approvals

Chemical composition (w%), typical, all weld metal

C	Mn	Si	Cr	Ni	Mo	Nb	FN
0.025	1.5	0.4	18.0	11.0	2.7	0.5	6-12

Mechanical properties, all weld metal

	Condition	0.2% Proof strength (N/mm ²)	Tensile strength (N/mm ²)	Elongation (%)	Impact ISO-V(J) +20°C
Required: AWS A5.4-92		not required	min. 550	min. 25	not required
EN 1600-97		min. 350	min. 550	min. 25	not required
Typical values	AW	430	650	30	90

Packaging, available sizes and identification

	Diameter (mm)	2.5	3.2	4.0
	Length (mm)	350	350	350
Unit: Box	Pieces / unit (nominal)	135	150	100
	Net weight/unit (kg)	2.6	4.8	4.6

Identification

Imprint: 318-15 / Jungo 318

Tip colour: red

Jungo® 318: rev. EN 15

Materials to be welded

Steel grades	EN 10088-1/-2	EN 102 13-4	W.Nr.	ASTM/ACI A240/A312/A351	UNS
Extra low carbon C <0.03%	X2 CrNiMo 17-12-2		1.4404	(TP)316L CF-3M	S31603 J92800
	X2 CrNiMo 18-14-3		1.4435	(TP)316L	S31603
	X2 CrNiMoN 17-11-2		1.4406	(TP)316LN	S31653
	X2 CrNiMoN 17-13-3		1.4429		
Medium carbon C >0.03%	X4 CrNiMo 17-12-2		1.4401	(TP)316	S31600
	X4 CrNiMo 17-13-3		1.4436		
Ti-, Nb stabilized		GX5 CrNiMo 19-11	1.4408	CF 8M	J92900
	X6 CrNiMoTi 17-12-2		1.4571	316Ti	S31635
	X6 CrNiMoNb 17-12-2		1.4580	316Cb	S31640
	X6 CrNiNb 18-10		1.4550	(TP)347	S34700
		GX5 CrNiNb 19-10	1.4552	CF-8C	J92710

Calculation data

Sizes Diam. x length (mm)	Current range type (A)	Current	Arc time - per electrode at max. current - (s)*	Energy E(kJ)	Dep.rate H(kg/h)	Weight/ 1000 pcs. (kg)	Electrodes/ kg weldmetal B	kg Electrodes/ kg weldmetal 1/N
2.5 x 350	50 - 70	DC+	50	86	0.82	17.6	88	1.89
3.2 x 350	80 - 100	DC+	51	135	1.3	28.5	53	1.72
4.0 x 350	100 - 130	DC+	66	206	1.7	43.8	32	1.56

* stub end 35mm

Welding parameters, optimum fill passes

Welding positions Diameter (mm)	PA/1G Current (A)	PB/2F	PC/2G	PF/3G up	PE/4G	PF/5G up
2.5	60	60	60	60	60	60
3.2	95	90	90	75	75	75
4.0	125	110	125	100	100	100

Remarks

Deviations: chemical composition:

Ni = 10.0 - 13.0%

AWS: Ni = 11.0 - 14.0%